



SURYA ALLOY INDUSTRIES LIMITED



Ferro Chrome



STANDARD GRADE

Cr	:	60%	Min
C	:	8%	Max
Si	:	3%	Max
P	:	0.03 / 0.04%	Max (As per Requirement)
S	:	0.05%	Max



LOW SILICON

Cr	:	60% / 65%	Min
C	:	9%	Max
Si	:	1% / 1.5%	Max (As per Requirement)
P	:	0.03%	Max
S	:	0.05%	Max



LOW TI

Cr	:	65%	Min
C	:	9%	Max
Si	:	1% / 1.5%	Max (As per Requirement)
P	:	0.03%	Max
S	:	0.05%	Max
Ti	:	0.02% / 0.03%	Max (As per Requirement)



LOW CARBON

Cr	:	65% / 70%	Min (As per Requirement)
C	:	0.1% / 0.2%	Max (As per Requirement)
Si	:	1.5%	Max
P	:	0.02%	Max
S	:	0.02%	Max



MEDIUM CARBON

Cr	:	65%	Min
C	:	0.5% - 4%	Max (As per Requirement)
Si	:	1.5%	Max
P	:	0.03 %	Max
S	:	0.03%	Max